

Data Sheet: FFKM3418

formerly 8714

MATERIAL: PERFLUOROELASTOMER 60 +/-5 SHORE

General use - with high chemical resistance.

COLOUR: WHITE

FFKM 60 ± 5 Shore A, white, high chemical resistance

Designed for use in very demanding conditions and in all industries

In compliance with FDA, CE and 3A requirements

Temperature resistance from - 10°C to + 230°C (+ 260°C short time)

PHYSICAL PROPERTIES	TEST METHOD	TEST RESULT
HARDNESS SHORE A	ISO 868	60
TENSILE STRENGTH, MPa	ISO 37	21
ELONGATION, %	ISO 37	180
MODULUS 100%,	ISO 37	10
COMPRESSION SET		
70 hrs@ 200°C %	ASTM D395/B	14
LOW TEMPERATURE FLEXIBILITY		
TR-10°C	ASTM D1329	-2
AIR AGEING, 70hrs @ 230°C		
HARDNESS CHANGE, SHORE A	ASTM D573	+1
TENSILE STRENGTH CHANGE, %	ASTM D573	+1
ELONGATION CHANGE, %	ASTM D573	+7.9
STEAM IMMERSION, 168hrs @ 220°C		
HARDNESS CHANGE, SHORE A	ASTM D471	+1
TENSILE STRENGTH CHANGE, %	ASTM D471	-19
ELONGATION CHANGE, %	ASTM D471	+36
VOLUME CHANGE, %	ASTM D471	+0.8
SULPHURIC ACID 98% IMMERSION, 70hrs @ 60°C		
HARDNESS CHANGE, SHORE A	ASTM D471	0
TENSILE STRENGTH CHANGE, %	ASTM D471	-5.3
ELONGATION CHANGE, %	ASTM D471	-12.2
VOLUME CHANGE, %	ASTM D471	+0.1
AMMONIA, ANHYDROUS IMMERSION, 500hrs @ 100°C		
HARDNESS CHANGE, SHORE A	ASTM D471	+6
TENSILE STRENGTH CHANGE, %	ASTM D471	-6.8
ELONGATION CHANGE, %	ASTM D471	-6.1
VOLUME CHANGE, %	ASTM D471	-0.4

Data Sheet: FFKM3418

formerly 8714

The above test results are based on test slabs / buttons. The results from the actual parts may be different.
ISSUE DATE 01/07/2017